

Characteristics and features

- EPDM quality
- sulfur cured
- lacquer indifferent
- complies with VW 2.8.1 G70
- complies with VW TL 52320
- complies with DBL 5571.10

A-KG 70-00

All our products are:

- PAH-free (EU 1272/2013)
- REACH conform
- Nitrosamin free
- RoHS II conform

Technical data sheet

Polymer		DIN ISO 1629	EPDM
Colour			black
Shore hardness	[ShA]	ISO 7619-1 / 3s	70 ± 5
Density	[g/cm ³]	DIN EN ISO 1183 / ISO 2781	1,23 ± 0,02
Tensile strength	[N/mm ²]	ISO 37	> 6,5
Elongation at break	[%]	ISO 37	> 250
Temperature resistance	[°C]		-55°C to +100°C
Tear strength	[N/mm]	DIN ISO 34-1 A	> 5,0
Compression set *	[%]	ISO 815	< 35
Fire resistance **		FMVSS 302	B (hardly inflammable)
Ozone resistance ***		ISO 1431-1	ozone resistant
Spec. Volume resistance	[Ωcm]	VDE 0303-30	conducting

* 24 h / 70 °C; ** tested at bei 2 mm; *** 50 pphm, 40°C, 72 h, 20% Elongation

Resistance



Stand: 20.10.2016 / issue: 1

Important information:

The listed test values and data are based on results of many years of development, tests and proving. A characteristics warranty and guaranteed function can't be derived from the information given. It is within the user's responsibility to test the selection of material in a specific application to ascertain his intended operational capability. Technical changes within the product development are subject to change.

This edition supersedes all previous data sheets.